

Serial No. 10/705,174  
 Response date September 14, 2006  
 Reply to Office Action of June 16, 2006

RECEIVED  
 CENTRAL FAX CENTER  
 SEP 14 2006

### AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application.

#### Listing of the Claims

1. (Currently Amended) A filter for providing potable water, comprising:
  - (a) a housing having an inlet and an outlet; and
  - (b) a filter material disposed within said housing formed at least in part from a plurality of mesoporous activated carbon filter particles and particles selected from the group consisting of mesoporous activated carbon filter particles coated entirely with a cationic polymer, mesoporous activated carbon filter particles partially coated with a cationic polymer, and mixtures thereof;

wherein the filter has a F-BLR Filter Bacteria Log Removal of greater than about 2 logs and a F-VLR Filter Viruses Log Removal of greater than about 1 log.
  
2. (Original) The filter of claim 1, wherein the cationic polymer is selected from the group consisting of: polyvinylamine, poly(N-methylvinylamine), polyallylamine, polyallyldimethylamine, polydiallylmethylamine, polydiallyldimethylamine, polydiallyldimethylammonium chloride, polyvinylpyridinium chloride, poly(2-vinylpyridine), poly(4-vinylpyridine), polyvinylimidazole, poly(4-aminomethylstyrene), poly(4-aminostyrene), polyvinyl(acrylamide-co-dimethylaminopropylacrylamide), polyvinyl(acrylamide-co-dimethylaminoethylmethacrylate), polyethyleneimine, polylysine, DAB-Am and PAMAM dendrimers, polyaminoamides, polyhexamethylenebiguandide, polydimethylamine-epichlorohydrine, aminopropyltriethoxysilane, N-(2-aminoethyl)-3-aminopropyltrimethoxysilane, N-trimethoxysilylpropyl-N, N, N-trimethylammonium chloride, bis(trimethoxysilylpropyl)amine, chitosan, grafted starch, the product of alkylation of polyethyleneimine by methylchloride, the product of alkylation of polyaminoamides with epichlorohydrine, cationic polyacrylamide with cationic monomers, dimethyl aminoethyl acrylate methyl chloride (AETAC), dimethyl aminoethyl methacrylate methyl chloride

Serial No. 10/705,174  
Response date September 14, 2006  
Reply to Office Action of June 16, 2006

(METAC), acrylamidopropyl trimethyl ammonium chloride (APTAC), methacryl amodopropyl trimethyl ammonium chloride (MAPTAC), diallyl dimethyl ammonium chloride (DADMAC), ionenes, silanes and mixtures thereof.

3. (Original) The filter of claim 1, wherein the cationic polymer is selected from the group consisting of: polyaminoamides, polyethyleneimine, polyvinylamine, polydiallyldimethylammonium chloride, polydimethylamine-epichlorohydrin, polyhexamethylenebiguanide, poly-[2-(2-ethoxy)-ethoxyethyl-guanidinium] chloride.

4 (Original) The filter of claim 1, wherein at least a portion of the mesoporous activated carbon filter particles, the mesoporous activated carbon filter particles coated entirely with a cationic polymer, or the mesoporous activated carbon filter particles partially coated with a cationic polymer are further coated with silver or a silver containing material.

5. (Original) The filter of claim 1, wherein the sum of the mesopore and the macropore volumes of said plurality of mesoporous activated carbon filter particles is between about 0.2 mL/g and about 2 mL/g.

6. (Currently Amended) The filter of claim 1, wherein said plurality of mesoporous activated carbon filter particles has a BRI Bacteria Removal Index of greater than about 99% and a VRI Viruses Removal Index of greater than about 90%.

7. (Canceled)

8. (Original) The filter of claim 1, wherein said filter material has a single-collector efficiency,  $\eta$ , of between about 0.005 and 0.25, and a filter coefficient,  $\lambda$ , between about 40 m<sup>-1</sup> and about 14,000 m<sup>-1</sup>.

Serial No. 10/705,174  
Response date September 14, 2006  
Reply to Office Action of June 16, 2006

9. (Currently Amended) The filter of claim 1, wherein said plurality of mesoporous activated carbon filter particles are basic and have a point of zero charge between about 9 and about 12, an ~~ORP~~ Oxidation Reduction Potential between about 290 mV and about 175 mV.
10. (Currently Amended) A filter for providing potable water, comprising:
- (a) a housing having an inlet and an outlet; and
  - (b) a filter material disposed within said housing formed at least in part from a plurality of mesoporous activated carbon filter particles and other materials selected from the group consisting of activated carbon powders, activated carbon granules, activated carbon fibers, zeolites, activated alumina, activated magnesia, diatomaceous earth, activated silica, hydrotalcites, glass, polyethylene fibers, polypropylene fibers, ethylene maleic anhydride copolymer fibers, sand, clay and mixtures thereof, wherein at least a portion of the mesoporous activated carbon filter particles are coated with a cationic polymer; wherein at least a portion of the other materials are coated with a material selected from the group consisting of silver, a silver containing material, a cationic polymer and mixtures thereof; wherein the filter has a ~~F-BLR~~ Filter Bacteria Log Removal of greater than about 2 logs and a ~~F-VLR~~ Filter Viruses Log Removal of greater than about 1 log.
11. (Canceled)
12. (Original) A kit comprising:
- i) a filter to claim 1; and
  - ii) a package for containing the filter; and wherein either the package or the filter housing comprises information that the filter or filter material provides: bacterial removal; virus removal; microbial removal; killing of bacteria, killing of viruses, killing of microbials, or any combination of these.
13. (Original) A kit comprising:
- i) a filter according to claim 10; and

Serial No. 10/705,174  
Response date September 14, 2006  
Reply to Office Action of June 16, 2006

ii) package for containing the filter; and wherein either the package or the filter housing comprises information that the filter or filter material provides: bacterial removal; virus removal; microbial removal; killing of bacteria, killing of viruses, killing of microbials, or any combination of these.

14. (Original) The filter of claim 4 where in the cationic polymer is selected from the group consisting of: polyaminoamides, polyethyleneimine, polyvinylamine, polydiallyldimethylammonium chloride, polydimethylamine-epichlorohydrin, polyhexamethylenebiguanide, poly-[2-(2-ethoxy)-ethoxyethyl-guanidinium] chloride.

15. (Currently Amended) A filter for providing potable water, comprising:

(a) a housing having an inlet and an outlet; and

(b) a filter material disposed within said housing formed at least in part from a plurality of mesoporous activated carbon filter particles

wherein at least a portion of said mesoporous activated carbon filter particles are at least partially coated with a cationic polymer;

~~wherein the filter is operable to remove bacteria, viruses, microbials, or any combination thereof from an influent passing through the filter~~ has a Filter Bacteria Log Removal of greater than about 2 logs and a Filter Viruses Log Removal of greater than about 1 log.